



HIGH DENSITY GAS PIPE

FEATURES:

- BARCODE printline per ASTM F2837 for DIMP compliance.
- Outstanding resistance to Slow Crack Growth (SCG) and Rapid Crack Propagation (RCP)
- High Performance Resin for Demanding Applications
- Manufactured in accordance with ASTM D2513
- Meets ASTM D3350 cell classification PE445574C
- Material grades PE4710/PE100 per PPI TR-4
- Industry leader in adoption of rework-free (7/2012)

SAMPLE PRINTLINE:

4" IPS SDR 11 - DURA-LINE POLYPIPE® GDB50 GAS - PE4710 - CEE - ASTM D2513 - D##J##NR - 3GA - 06JAN17 - COIL XX ###FT

APPLICATION:

Natural Gas Distribution

SIZE RANGE:

1/2" - 1" CTS & 1/2" - 12" IPS. Contact Dura-Line for additional sizes.

COLOR/STRIPE:

Black or Black with Yellow Stripe



PolyPipe® is manufactured with high performance resins engineered with outstanding resistance to Slow Crack Growth (SCG) and Rapid Crack Propagation (RCP). These unique properties bring outstanding integrity for gas distribution systems. Dura-Line is ISO 9001 certified and PolyPipe® is qualified using exacting laboratory procedures and test methods, and a consistent uncompromised quest for design and manufacturing excellence.



High Density PolyPipe for Gas Distribution is manufactured using bimodal HDPE resin for enhanced performance properties.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	ASTM TEST METHOD	*NOMINAL VALUES
		Bi-Modal PE4710
Density, Natural	D1505	0.949 gm/cc
Density, Black	D1505	0.960 gm/cc
Melt Index (190°C/2.16 kg)	D1238	0.08 gm/10 min.
Flow Rate (190°C/21.6 kg)	D1238	7.5 gm/10 min.
Tensile Strength @ Yield	D638	3,600 psi
Ultimate Elongation	D638	>500%
Flexural Modulus – 2% Secant	D790	150,000 psi
Resistance to Rapid Crack Propagation, Full Scale Pc @ 0°C	ISO 13478	>665 psi
Resistance to Rapid Crack Propagation, S-4 Pc @ 0°C	ISO 13477	>174 psi
Resistance to Rapid Crack Propagation, S-4 Tc @ 10 bar	ISO 13477	<2°F
PENT	F1473	>5,000 hrs.
Hardness, Shore D	D2240	64
Izod Impact Strength (Notched)	D256	8 ft-lbf/in
Vicat Softening Temperature	D1525	255°F
Volume Resistivity	D991	>1015 ohm-cm
Thermal Expansion Coefficient	D696	1.0 x 10 ⁻⁴ in/in/°F
CELL CLASSIFICATION	D3350	445574C / 445576C
PPI HYDROSTATIC DESIGN BASIS (HDB) (as listed in PPI TR-4)	D2837	1,600 psi @ 73.4°F 1,000 psi @ 140°F

*Nominal values are intended to be guides only, and not as specification limit. Specific values may vary based upon resin compound.

*Some of the data listed above was determined from compression molded test specimens; therefore may deviate from pipe specimens.



PE4710/PE100

GAS PIPE DATA AND PRESSURE RATINGS – CTS & IPS

NOMINAL PE SIZE, INCHES	DR	DESIGN PRESSURE RATING* FOR NATURAL GAS, PSIG @ 73°F	DIMENSIONS		STANDARD LENGTH, FT	WEIGHT, LBS/FT
			Average OD, inches	Min. Wall Thickness, inches		
CTS ½	–	100	0.625	0.090	1,000	0.066
1	–	100	1.125	0.090	500	0.128
IPS ½	9.3	100	0.840	0.090	500	0.093
¾	11	100	1.050	0.095	500	0.126
1	11	100	1.315	0.120	500	0.197
1¼	10	100	1.650	0.165	500	0.341
1 ¼	11	100	1.650	0.150	500	0.314
1 ½	11	100	1.900	0.173	500	0.411
2	11	100	2.375	0.216	250	0.642
2	11	100	2.375	0.216	500	0.642
2	11	100	2.375	0.216	1,500	0.642
3	9	125	3.500	0.389	40	1.664
3	11	100	3.500	0.318	500	1.395
3	11	100	3.500	0.318	40	1.395
4	9	125	4.500	0.500	40	2.751
4	11	100	4.500	0.409	40	2.306
6	9	125	6.625	0.736	40	5.963
6	11	100	6.625	0.602	40	4.997
8	9	125	8.625	0.958	40	10.106
8	11	100	8.625	0.784	40	8.470
10	9	125	10.750	1.194	40	15.700
10	11	100	10.750	0.977	40	13.157
12	9	125	12.750	1.417	40	22.085
12	11	100	12.750	1.159	40	18.508

Ratings are in accordance with DOT CFR 49, Part 192, §192.121 and §192.123.

Effective July 14, 2004, the maximum design pressure was amended to 125 psig (reference §192.123a) when designed in accordance with §192.121 for nominal pipe sizes up through 12"IPS (§192.123e.3).

NOTES:

- Some sizes are special order. Call for availability on sizes or DR's not shown.
- The above weights are calculated per PPI TR-7, using a density of 0.960.